

IN THE CLAIMS:

Claims 1-14 cancelled

15. (New) A thermoplastic molding composition comprising

- a) 60-65 parts by weight of a poly(ester) carbonate,
- b) 3-20 parts by weight of a graft polymer having a graft base and
- c) 5-20 parts by weight of a member selected from the group consisting of polyethylene naphthalate and polyethylene naphthalate co-terephthalate.

16. (New) The composition of Claim 15 wherein the graft polymer has average particle diameter ( $d_{50}$ ) of 0.5 to 5  $\mu\text{m}$ .

17. (New) The composition of Claim 16 wherein the average particle diameter is 0.5 to 2.5  $\mu\text{m}$ .


18. (New) The composition of Claim 16 wherein the average particle diameter is 0.1 to 0.5  $\mu\text{m}$ .

19. (New) The composition if Claim 15 further containing at least one member selected from the group consisting of vinyl copolymer and polyalkylene terephthalate.

20. (New) The composition of Claim 15 wherein the graft base is at least one rubber selected from the group consisting of diene, EP(D)M, acrylate, polyurethane, silicone, chloroprene and ethylene/vinyl acetate.

21. (New) The composition of Claim 15 further containing at least one member selected from the group consisting of flame retardant, stabilizer, pigment, mold release agent, flow auxiliary and antistatic agent.

22. (New) The composition of Claim 21 wherein the flame retardant is a phosphates conforming to formula (IV)



in which

$\text{R}^5$ ,  $\text{R}^6$ ,  $\text{R}^7$  and  $\text{R}^8$  independently of one another denote a member selected from the group consisting of  $\text{C}_1$ - $\text{C}_8$  alkyl,  $\text{C}_5$ - $\text{C}_6$  cycloalkyl,  $\text{C}_6$ - $\text{C}_{30}$  aryl and  $\text{C}_7$ - $\text{C}_{12}$  aralkyl,

X denotes a mono- or polycyclic aromatic radical having 6 to 30 C atoms,

k independently of one another is 0 or 1 and

N is 0 to 30.

23. (New) The composition of Claim 22 wherein the  $\text{C}_1$ - $\text{C}_8$  alkyl is halogenated.

24. (New) The composition of Claim 22 wherein at least one member selected from the group consisting of  $\text{C}_5$ - $\text{C}_6$  cycloalkyl,  $\text{C}_6$ - $\text{C}_{30}$  aryl or  $\text{C}_7$ - $\text{C}_{12}$  aralkyl is alkyl and/or halogen-substituted.

25. (New) A method of using the composition of Claim 15 comprising forming a molded article.

26. (New) A molded article comprising the composition of Claim 15.